

Obduce


BASIC INFORMATION

Launch Date	01/04/2019	Tariff item number	54077300
Delivery time (weeks) special lab dip	4	Number of colour ways	10
Country of origin	Turkey	Characteristics	Sheer
Vertical repeat (cm)	Plain	Vertical repeat (inch)	Plain
Horizontal repeat (cm)	Plain	Horizontal repeat (inch)	Plain
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Double folded face in	Yes	Minimum for special colour (m)	500
Average piece length (m)	50	MID	TRTEXTRABUR

CATEGORY

Colouring type	Yarn dyed	Treatment	Calender
Type of print/dye - disperse	Yes	Zinc selvedge	Yes
After treatment - zinc selvedge weight (g/m)	22		

Care codes

Care code for washing (°C)	Wash at 71°C	Care code for washing (°F)	Wash at 160°F
   			

Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
-------------------------------	-----	----------	-----

FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	84.21
Weaving type - jacquard	Yes	Construction	22x41.8
Useable width (cm)	305.00	Useable width (inch)	120.08
Full width (cm)	307	Full width (inch)	120.87
Woven	Yes	Weight (g/m ²)	76

FR STANDARDS

AATCC 96 (Complies)	Yes	AS/NZS 1530.2 (Pass)	Yes
AS/NZS 1530.3 (Pass)	Yes	BS5867 part 2 type B	Yes
BS5867 part 2 type C (Complies)	Yes	Boston Fire test BFD IX-1 (Pass)	Yes
CAL 19 section 1237.1	Yes	DIN 4102 (B1)	Yes
EN13773	Yes	IMO FTPC PART 7: Textiles and films	Yes
Japanese L1091	Yes	M1 France	Yes

NFPA 701	Yes	NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes
SN 198'898 (Class 5.2)	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

SPECIFICATIONS

Colour fastness to light	6	Wyzenbeek (double rubs)	5000
Wyzenbeek cotton duck type unrated	Yes	Acoustic absorption ISO 354 - ISO 11654	E/NA

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	0.53-	Dimensional change warp after ironing	0.46-
Dimensional change weft	0.17	Dimensional change weft after ironing	0.20-
Colour fastness (ISO 105 C06)	5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	2.22-	Dimensional change warp after ironing	1.26-
Dimensional change weft	0.40-	Dimensional change weft after ironing	0.13-
Colour fastness (ISO 105 C06)	4-5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	0.79-	Dimensional change warp after ironing	0.40-
Dimensional change weft	0.43-	Dimensional change weft after ironing	0.46-
Colour fastness (ISO 105 D01)	4		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.02	Dimensional change warp after ironing without steam	0.00
Dimensional change warp after ironing with steam		Dimensional change weft	0.08

	0.80-		
Dimensional change weft after ironing without steam		Dimensional change weft after ironing with steam	
	0.00		0.07-

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester inherent FR	Warp yarn sizes	70D
Warp threads per cm	22.00	Warp turns per meter (TPM)	0
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

Yarn 2

Weft composition	100% Polyester inh	Weft yarn sizes	NE20/1
Weft threads per cm	16.80	Weft turns per meter (TPM)	0
Weft type filament	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

Yarn 3

Weft composition	100% Polyester inh	Weft yarn sizes	75D
Weft threads per cm	8.40	Weft turns per meter (TPM)	0
Weft type filament	Yes		
Weft specification textured	Yes	Weft not high tenacity	Yes

Yarn 4

Weft composition	100% Polyester inh	Weft yarn sizes	300D
Weft threads per cm	4.20	Weft turns per meter (TPM)	100
Weft type filament	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

Yarn 5

Weft composition	100% Polyester inh	Weft yarn sizes	150D
Weft threads per cm	4.20	Weft turns per meter (TPM)	200
Weft type filament	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

Yarn 6

Weft composition	100% Polyester inh	Weft yarn sizes	70D
Weft threads per cm	8.40	Weft turns per meter (TPM)	0
Weft type filament	Yes		

Technical Product Summary



Weft specification textured

Yes

Weft not high tenacity

Yes