

Oscillate





BASIC INFORMATION

Launch Date	01/04/2019	Tariff item number	54079300
Delivery time (weeks) special lab dip	4	Number of colour ways	5
Country of origin	Turkey	Characteristics	Sheer
Vertical repeat (cm)	stripe	Vertical repeat (inch)	stripe
Horizontal repeat (cm)	1.40	Horizontal repeat (inch)	0.55
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Double folded face in	Yes	Minimum for special colour (m)	500
Average piece length (m)	50	MID	TRTEXTRABUR

CATEGORY

Colouring type	Yarn dyed	Treatment	Calender
Type of print/dye - disperse	Yes	Zinc selvedge	Yes
After treatment - zinc selvedge weight (g/m)	22		

Care codes

Care code for washing (°C)	Wash at 71°C	Care code for washing (°F)	Wash at 160°F
   			

Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
-------------------------------	-----	----------	-----

FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	67.5
Weaving type - jacquard	Yes	Construction	22x31
Useable width (cm)	305.00	Useable width (inch)	120.08
Full width (cm)	307	Full width (inch)	120.87
Woven	Yes	Weight (g/m²)	80

FR STANDARDS

AATCC 96 (Complies)	Yes	AS/NZS 1530.2 (Pass)	Yes
AS/NZS 1530.3 (Pass)	Yes	BS5867 part 2 type B	Yes
BS5867 part 2 type C (Complies)	Yes	Boston Fire test BFD IX-1 (Pass)	Yes
CAL 19 section 1237.1	Yes	CAN/ULC-S109 Large flame test	Yes
CAN/ULC-S109 Small flame test	Yes	DIN 4102 (B1)	Yes
EN13773	Yes	FMVSS 302 (Pass)	Yes

IMO FTPC PART 7: Textiles and films	Yes	Japanese L1091	Yes
M1 France	Yes	NFPA 701	Yes
NY/NJ Port Authority - FAR 25.853 12 (Pass)		SN 198'898 (Class 5.2)	Yes
	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

SPECIFICATIONS

Colour fastness to light	6	Acoustic absorption ISO 354 - ISO 11654	E/NA
--------------------------	---	---	------

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Resistance to domestic washing 30°C (indicated in %) - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	0.60-	Dimensional change warp after ironing	0.53-
Dimensional change weft	0.17-	Dimensional change weft after ironing	0.07
Colour fastness (ISO 105 C06)	4-5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	2.74-	Dimensional change warp after ironing	1.85-
Dimensional change weft	0.43-	Dimensional change weft after ironing	0.27-
Colour fastness (ISO 105 C06)	4-5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	1.78-	Dimensional change warp after ironing	1.65-
Dimensional change weft	0.79-	Dimensional change weft after ironing	0.79-
Colour fastness (ISO 105 D01)	4-5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.17	Dimensional change warp after ironing without steam	0.07-
Dimensional change warp after ironing with steam	1.20-	Dimensional change weft	0.08-
Dimensional change weft after ironing without steam	0.13	Dimensional change weft after ironing with steam	0.20-

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester inherent FR	Warp yarn sizes	70D
Warp threads per cm	22.00	Warp turns per meter (TPM)	0
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

Yarn 2

Weft composition	100% Polyester inherent FR	Weft yarn sizes	70D
Weft threads per cm	11.52	Weft turns per meter (TPM)	0
Weft type filament	Yes		
Weft specification textured	Yes	Weft not high tenacity	Yes

Yarn 3

Weft composition	100% Polyester inherent F	Weft yarn sizes	150D
Weft threads per cm	7.68	Weft turns per meter (TPM)	200
Weft type filament	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

Yarn 4

Weft composition	100% Polyester inherent F	Weft yarn sizes	1600D
Weft threads per cm	0.64	Weft turns per meter (TPM)	0
Weft type filament	Yes		
Weft specification textured	Yes	Weft specification not textured	Yes
Weft not high tenacity	Yes		

Yarn 5

Weft composition	100% Polyester inherent F	Weft yarn sizes	75D
Weft threads per cm	12.16	Weft turns per meter (TPM)	0
Weft type filament	Yes		



Weft specification textured

Yes

Weft not high tenacity

Yes