

Jaborine

BASIC INFORMATION

| | | | |
|---------------------------------------|------------|---------------------------------------|-------------|
| Launch Date | 01/04/2017 | Tariff item number | 54079300 |
| Delivery time (weeks) special lab dip | 4 | Number of colour ways | 4 |
| Country of origin | Turkey | Characteristics | Jacquard |
| Vertical repeat (cm) | 29.00 | Vertical repeat (inch) | 11.42 |
| Horizontal repeat (cm) | 29.00 | Horizontal repeat (inch) | 11.42 |
| Roll diameter (in cm, for 50 meters) | 0 | Roll diameter (in inch, for 50 meter) | 0 |
| Face in | Yes | Minimum for special colour (m) | 1000 |
| Average piece length (m) | 50 | MID | TRTEXTRABUR |

CATEGORY

| | | | |
|------------------------|-----------|-----------|------------|
| Colouring type | Yarn dyed | Treatment | Sanforized |
| After treatment - none | Yes | | |

Care codes

Care code for washing (°F)

Wash at 140°F gentle cycle



Use codes

| | | | |
|-------------------------------|-----|------------------------|-----|
| Use code - curtains/draperies | Yes | Use code - accessories | Yes |
|-------------------------------|-----|------------------------|-----|

FABRIC TYPE

| | | | |
|-------------------------|----------------------------|----------------------|-------|
| Composition | 100% Polyester inherent FR | Average yarn number | 44.62 |
| Weaving type - jacquard | Yes | Construction | 80x36 |
| Useable width (cm) | 145.00 | Useable width (inch) | 57.09 |
| Full width (cm) | 147 | Full width (inch) | 57.87 |
| Woven | Yes | Weight (g/m²) | 260 |

FR STANDARDS

| | | | |
|---------------------------------|-----|----------------------------------|-----|
| AATCC 96 (Complies) | Yes | AS/NZS 1530.2 (Pass) | Yes |
| AS/NZS 1530.3 (Pass) | Yes | BS5867 part 2 type B | Yes |
| BS5867 part 2 type C (Complies) | Yes | Boston Fire test BFD IX-1 (Pass) | Yes |
| CAL 19 section 1237.1 | Yes | CAN/ULC-S109 Large flame test | Yes |
| CAN/ULC-S109 Small flame test | Yes | DIN 4102 (B1) | Yes |
| EN13773 | Yes | FMVSS 302 (Pass) | Yes |

| | | | |
|---|-----|------------------------|-----|
| IMO FTPC PART 7: Textiles and films | Yes | Japanese L1091 | Yes |
| M1 France | Yes | NFPA 701 | Yes |
| NY/NJ Port Authority - FAR 25.853 12 (Pass) | Yes | SN 198'898 (Class 5.2) | Yes |
| UNI 9174 Classe Uno (Pass) | Yes | | |

ENVIRONMENTAL STANDARDS

| | | | |
|----------|-----|-----------|-----|
| Oeko-Tex | Yes | ISO 14001 | Yes |
|----------|-----|-----------|-----|

SPECIFICATIONS

| | | | |
|--------------------------|-----|---|-----|
| Colour fastness to light | 5 | Pilling | 4-5 |
| Brush pilling | 4-5 | Acoustic absorption ISO 354 - ISO 11654 | |
| | | draped C/flat D | |

Colour fastness to light - ISO 105-B02

| | |
|--------------------------|---|
| Colour fastness to light | 5 |
|--------------------------|---|

Colour fastness to water - ISO 105-E01

| | |
|--------------------------|---|
| Colour fastness to water | 5 |
|--------------------------|---|

Colour fastness to dry rub - ISO 105-X12

| | |
|-------------------------|---|
| Colour fastness dry rub | 4 |
|-------------------------|---|

Colour fastness to wet rub - ISO 105-X12

| | |
|-------------------------|-----|
| Colour fastness wet rub | 4-5 |
|-------------------------|-----|

Elongation - ISO 13934-1

| | | | |
|---------------------|----|---------------------|----|
| Elongation warp (%) | 32 | Elongation weft (%) | 22 |
|---------------------|----|---------------------|----|

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

| | | | |
|-------------------------------|-------|---------------------------------------|-------|
| Dimensional change warp | 2.16- | Dimensional change warp after ironing | 2.00- |
| Dimensional change weft | 0.33- | Dimensional change weft after ironing | 0.33- |
| Colour fastness (ISO 105 C06) | 5 | | |

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

| | | | |
|-------------------------------|-------|---------------------------------------|-------|
| Dimensional change warp | 1.19- | Dimensional change warp after ironing | 0.99- |
| Dimensional change weft | 0.23- | Dimensional change weft after ironing | 0.20- |
| Colour fastness (ISO 105 D01) | 5 | | |

Dimensional stability (indicated in %) - ISO 3759

| | | | |
|---|-------|---|-------|
| Dimensional change warp | 0.21- | Dimensional change warp after ironing without steam | 0.07 |
| Dimensional change warp after ironing with steam | 0.13- | Dimensional change weft | 0.08- |
| Dimensional change weft after ironing without steam | 0.00 | Dimensional change weft after ironing with steam | 0.20 |

CONSTRUCTION

Yarn 1

| | | | |
|-----------------------------|----------------------------|----------------------------|-----|
| Warp composition | 100% Polyester inherent FR | Warp yarn sizes | 75d |
| Warp threads per cm | 80.00 | Warp turns per meter (TPM) | 550 |
| Warp type filament | Yes | | |
| Warp specification textured | Yes | Warp not high tenacity | Yes |

Yarn 2

| | | | |
|---------------------------------|----------------------------|----------------------------|------|
| Weft composition | 100% Polyester inherent FR | Weft yarn sizes | 300d |
| Weft threads per cm | 18.00 | Weft turns per meter (TPM) | 100 |
| Weft type filament | Yes | | |
| Weft specification not textured | Yes | Weft not high tenacity | Yes |

Yarn 3

| | | | |
|---------------------------------|----------------------------|----------------------------|---------|
| Weft composition | 100% Polyester inherent FR | Weft yarn sizes | Ne 20/2 |
| Weft threads per cm | 18.00 | Weft turns per meter (TPM) | 450 |
| Weft type staple | Yes | | |
| Weft specification not textured | Yes | Weft not high tenacity | Yes |