

# Jacadi

## BASIC INFORMATION

Launch Date	01/04/2017	Tariff item number	55151290
Delivery time (weeks) special lab dip	4	Number of colour ways	20
Country of origin	Turkey	Characteristics	Flat Weave
Vertical repeat (cm)	plain	Vertical repeat (inch)	plain
Horizontal repeat (cm)	plain	Horizontal repeat (inch)	plain
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	50	MID	TRTEXTRABUR

## CATEGORY

Colouring type	Yarn dyed	Treatment	Calender
After treatment - none	Yes		

### Care codes

Care code for washing (°F)

Wash at 105°F gentle cycle



### Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
Use code - upholstery	Yes	Use code - bed covering	Yes
Use code - accessories	Yes		

## FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	5.96
Weaving type - dobby	Yes	Construction	14x12.5
Useable width (cm)	140.00	Useable width (inch)	55.12
Full width (cm)	142	Full width (inch)	55.91
Woven	Yes	Weight (g/m²)	445

## FR STANDARDS

AATCC 96 (Complies)	Yes	ASTM E84 class I or A	Yes
AS/NZS 1530.2 (Pass)	Yes	AS/NZS 1530.3 (Pass)	Yes
BS5867 part 2 type B	Yes	BS5867 part 2 type C (Complies)	Yes
Boston Fire test BFD IX-1 (Pass)	Yes	BS5852 source 0	Yes

BS5852 source 1 comment	Yes, with FR coating	CAL 117 (Complies)	Yes
CAL 19 section 1237.1	Yes	CAN/ULC-S109 Large flame test	Yes
CAN/ULC-S109 Small flame test	Yes	Chinese GB-20286	Yes
DIN 4102 (B1)	Yes	EN13773	Yes
EN 1021 part 1 and 2	Yes	FMVSS 302 (Pass)	Yes
IMO A652 part 8	Yes	IMO FTPC PART 7: Textiles and films	Yes
M1 France	Yes	NFPA 260	Yes
NFPA 701	Yes	NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes
SN 198'898 (Class 5.2)	Yes	UNI 9174 Classe Uno (Pass)	Yes

## ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

## SPECIFICATIONS

Martindale (rubs)	70000	Colour fastness to light	6
Pilling	4	Brush pilling	4
Acoustic absorption ISO 354 - ISO 11654 draped C/flat C			

### Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

### Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

### Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

### Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

### Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4-5
-------------------------	-----

### Tearing strength - ISO 13937-3

Tearing strength warp (N)	110	Tearing strength weft (N)	150
---------------------------	-----	---------------------------	-----

**Tensile strength - ISO 13934-1**

Tensile strength warp (N/5cm)	2000	Tensile strength weft (N/5cm)	1600
-------------------------------	------	-------------------------------	------

**Elongation - ISO 13934-1**

Elongation warp (%)	26.5	Elongation weft (%)	26.5
---------------------	------	---------------------	------

**Seam slippage - ISO 13936-2**

Seam slippage warp (mm)	3	Seam slippage weft (mm)	4
-------------------------	---	-------------------------	---

**Resistance to domestic washing 40°C (indicated in %) - ISO 6330**

Dimensional change warp	1.86-	Dimensional change warp after ironing	1.46-
Dimensional change weft	0.57-	Dimensional change weft after ironing	0.33-
Colour fastness (ISO 105 C06)	5		

**Resistance to domestic washing 60°C (indicated in %) - ISO 6330**

Dimensional change warp	2.67-	Dimensional change warp after ironing	2.33-
Dimensional change weft	0.33-	Dimensional change weft after ironing	0.27-
Colour fastness (ISO 105 C06)	5		

**Resistance to dry cleaning P (indicated in %) - ISO 105 D01**

Dimensional change warp	1.85-	Dimensional change warp after ironing	1.59-
Dimensional change weft	0.50-	Dimensional change weft after ironing	0.46-
Colour fastness (ISO 105 D01)	5		

**Dimensional stability (indicated in %) - ISO 3759**

Dimensional change warp	0.29-	Dimensional change warp after ironing without steam	0.20
Dimensional change warp after ironing with steam	0.13-	Dimensional change weft	0.15-
Dimensional change weft after ironing without steam	0.07	Dimensional change weft after ironing with steam	0.60

**CONSTRUCTION**

**Yarn 1**

---

Warp composition	100% Poyester inherent FR	Warp yarn sizes	1445d
Warp threads per cm	14.00	Warp turns per meter (TPM)	NA
Warp type staple	Yes	Warp type filament	Yes
Warp specification textured	Yes	Warp specification not textured	Yes
Warp not high tenacity	Yes		

**Yarn 2**

---

Weft composition	100% Poyester inherent FR	Weft yarn sizes	1445d
Weft threads per cm	4.17	Weft turns per meter (TPM)	NA
Weft type staple	Yes	Weft type filament	Yes
Weft specification textured	Yes	Weft specification not textured	Yes
Weft not high tenacity	Yes		

**Yarn 3**

---

Weft composition	100% Poyester inherent FR	Weft yarn sizes	1221d
Weft threads per cm	8.33	Weft turns per meter (TPM)	NA
Weft type staple	Yes	Weft type filament	Yes
Weft specification textured	Yes	Weft specification not textured	Yes
Weft not high tenacity	Yes		