

# Jager

## BASIC INFORMATION

Launch Date	01/04/2017	Tariff item number	55151290
Delivery time (weeks) special lab dip	4	Number of colour ways	4
Country of origin	Turkey	Characteristics	Jacquard
Vertical repeat (cm)	32.00	Vertical repeat (inch)	12.60
Horizontal repeat (cm)	35.00	Horizontal repeat (inch)	13.78
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	50	MID	TRTEXTRABUR

## CATEGORY

Colouring type	Yarn dyed	Treatment	Thermofixed
After treatment - none	Yes		

### Care codes

Care code for washing (°F)

Wash at 140°F gentle cycle



### Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
Use code - accessories	Yes		

## FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	57.3
Weaving type - jacquard	Yes	Construction	66x40
Useable width (cm)	142.00	Useable width (inch)	55.91
Full width (cm)	144	Full width (inch)	56.69
Woven	Yes	Weight (g/m <sup>2</sup> )	185

## FR STANDARDS

AATCC 96 (Complies)	Yes	AS/NZS 1530.2 (Pass)	Yes
AS/NZS 1530.3 (Pass)	Yes	BS5867 part 2 type B	Yes
BS5867 part 2 type C (Complies)	Yes	Boston Fire test BFD IX-1 (Pass)	Yes
CAL 19 section 1237.1	Yes	CAN/ULC-S109 Large flame test	Yes
CAN/ULC-S109 Small flame test	Yes	DIN 4102 (B1)	Yes

EN13773	Yes	FMVSS 302 (Pass)	Yes
IMO FTPC PART 7: Textiles and films	Yes	Japanese L1091	Yes
M1 France	Yes	NFPA 701	Yes
NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes	SN 198'898 (Class 5.2)	Yes
UNI 9174 Classe Uno (Pass)	Yes		

## ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

## SPECIFICATIONS

Colour fastness to light	6	Pilling	3
Brush pilling	3	Acoustic absorption ISO 354 - ISO 11654	
		draped C/flat D	

### Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

### Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

### Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

### Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

### Elongation - ISO 13934-1

Elongation warp (%)	31	Elongation weft (%)	20.5
---------------------	----	---------------------	------

### Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	0.93-	Dimensional change warp after ironing	0.86-
Dimensional change weft	0.40-	Dimensional change weft after ironing	0.47-
Colour fastness (ISO 105 C06)	5		

**Resistance to domestic washing 60°C (indicated in %) - ISO 6330**

Dimensional change warp	1.60-	Dimensional change warp after ironing	1.46-
Dimensional change weft	0.77-	Dimensional change weft after ironing	0.73-
Colour fastness (ISO 105 C06)	5		

**Resistance to dry cleaning P (indicated in %) - ISO 105 D01**

Dimensional change warp	0.76-	Dimensional change warp after ironing	0.93-
Dimensional change weft	0.36-	Dimensional change weft after ironing	0.40-
Colour fastness (ISO 105 D01)	5		

**Dimensional stability (indicated in %) - ISO 3759**

Dimensional change warp	0.02	Dimensional change warp after ironing without steam	0.20
Dimensional change warp after ironing with steam	0.13-	Dimensional change weft	0.08-
Dimensional change weft after ironing without steam	0.00	Dimensional change weft after ironing with steam	0.00

**CONSTRUCTION**

**Yarn 1**

Warp composition	100% Polyester inherent FR	Warp yarn sizes	20d
Warp threads per cm	66.00	Warp turns per meter (TPM)	NA
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

**Yarn 2**

Weft composition	100% Polyester inherent FR	Weft yarn sizes	300d
Weft threads per cm	10.00	Weft turns per meter (TPM)	100
Weft type filament	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

**Yarn 3**

Weft composition	100% Polyester inherent FR	Weft yarn sizes	Ne 30/2
Weft threads per cm	10.00	Weft turns per meter (TPM)	600
Weft type staple	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

**Yarn 4**

Weft composition	100% Polyester inherent FR	Weft yarn sizes	Ne 30/2
Weft threads per cm	10.00	Weft turns per meter (TPM)	600
Weft type staple	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

---

**Yarn 5**

---

Weft composition	100% Polyester inherent FR	Weft yarn sizes	Ne 15/1
Weft threads per cm	10.00	Weft turns per meter (TPM)	650
Weft type staple	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes