

Jaipur

BASIC INFORMATION

Launch Date	01/04/2017	Tariff item number	55121990
Delivery time (weeks) special lab dip	4	Number of colour ways	3
Country of origin	Turkey	Characteristics	Sheer
Vertical repeat (cm)	plain	Vertical repeat (inch)	plain
Horizontal repeat (cm)	plain	Horizontal repeat (inch)	plain
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Double folded face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	50	Railroaded	Yes
MID	TRTEXTRABUR		

CATEGORY

Colouring type	Yarn dyed	Treatment	Thermofixed
After treatment - none	Yes		

Care codes

Care code for washing (°F)

Wash at 105°F gentle cycle



Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
Use code - accessories	Yes		

FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	9.41
Weaving type - dobby	Yes	Construction	8x8
Useable width (cm)	300.00	Useable width (inch)	118.11
Full width (cm)	302	Full width (inch)	118.9
Woven	Yes	Weight (g/m ²)	170

FR STANDARDS

AATCC 96 (Complies)	Yes	AS/NZS 1530.2 (Pass)	Yes
AS/NZS 1530.3 (Pass)	Yes	BS5867 part 2 type B	Yes
BS5867 part 2 type C (Complies)	Yes	Boston Fire test BFD IX-1 (Pass)	Yes
CAL 19 section 1237.1	Yes	CAN/ULC-S109 Large flame test	Yes

CAN/ULC-S109 Small flame test	Yes	DIN 4102 (B1)	Yes
EN13773	Yes	FMVSS 302 (Pass)	Yes
IMO FTPC PART 7: Textiles and films	Yes	Japanese L1091	Yes
M1 France	Yes	NFPA 701	Yes
NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes	SN 198'898 (Class 5.2)	Yes
UNI 9174 Classe Uno (Pass)	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

SPECIFICATIONS

Colour fastness to light	6	Acoustic absorption ISO 354 - ISO 11654 draped E/flat NA	
--------------------------	---	---	--

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Elongation - ISO 13934-1

Elongation warp (%)	15	Elongation weft (%)	19.5
---------------------	----	---------------------	------

Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	0.80-	Dimensional change warp after ironing	0.86-
Dimensional change weft	0.93-	Dimensional change weft after ironing	0.73-
Colour fastness (ISO 105 C06)	5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	1.96-	Dimensional change warp after ironing	1.73-
Dimensional change weft	1.06-	Dimensional change weft after ironing	1.06-
Colour fastness (ISO 105 C06)	5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	1.52-	Dimensional change warp after ironing	1.58-
-------------------------	-------	---------------------------------------	-------

Dimensional change weft	1.03-	Dimensional change weft after ironing	0.73-
Colour fastness (ISO 105 D01)	5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.21-	Dimensional change warp after ironing without steam	0.13
Dimensional change warp after ironing with steam	0.47-	Dimensional change weft	0.22-
Dimensional change weft after ironing without steam	0.13	Dimensional change weft after ironing with steam	0.53

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester inherent FR	Warp yarn sizes	Ne 6/1
Warp threads per cm	8.00	Warp turns per meter (TPM)	NA
Warp type staple	Yes		
Warp specification not textured	Yes	Warp not high tenacity	Yes

Yarn 2

Weft composition	100% Polyester inherent FR	Weft yarn sizes	Ne 6/1
Weft threads per cm	8.00	Weft turns per meter (TPM)	NA
Weft type staple	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes