

Lineal

BASIC INFORMATION

Launch Date	01/04/2018	Tariff item number	55151290
Delivery time (weeks) special lab dip	4	Number of colour ways	5
Country of origin	Turkey	Characteristics	Sheer
Vertical repeat (cm)	Stripe	Vertical repeat (inch)	Stripe
Horizontal repeat (cm)	12.00	Horizontal repeat (inch)	4.72
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Double folded face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	50	Railroaded	Yes
MID	TRTEXTRABUR		

CATEGORY

Colouring type	Yarn dyed	Treatment	Thermofixed
Type of print/dye - disperse	Yes	Zinc selvedge	Yes
After treatment - zinc selvedge weight (g/m)	22		

Care codes

Care code for washing (°C)	Wash at 71°C	Care code for washing (°F)	Wash at 160°F
Care code comments			
also washable at 71°C /160F meeting American hospital washing standard AATCC96			



Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
-------------------------------	-----	----------	-----

FABRIC TYPE

Composition	100% Polyester Inherent FR	Average yarn number	170.21
Weaving type - jacquard	Yes	Construction	40x40
Useable width (cm)	300.00	Useable width (inch)	118.11
Full width (cm)	302	Full width (inch)	118.9
Woven	Yes	Weight (g/m²)	47

FR STANDARDS

AS/NZS 1530.2 (Pass)	Yes	AS/NZS 1530.3 (Pass)	Yes
BS5867 part 2 type B	Yes	BS5867 part 2 type C (Complies)	Yes

Boston Fire test BFD IX-1 (Pass)	Yes	CAL 19 section 1237.1	Yes
DIN 4102 (B1)	Yes	FMVSS 302 (Pass)	Yes
IMO FTPC PART 7: Textiles and films	Yes	M1 France	Yes

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

SPECIFICATIONS

Colour fastness to light	6	Acoustic absorption ISO 354 - ISO 11654 draped D/ flat n.a.
--------------------------	---	--

Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	0.63-	Dimensional change warp after ironing	0.40-
Dimensional change weft	0.33-	Dimensional change weft after ironing	0.33-
Colour fastness (ISO 105 C06)	5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	0.36-	Dimensional change warp after ironing	0.33-
Dimensional change weft	0.26-	Dimensional change weft after ironing	0.26-
Colour fastness (ISO 105 D01)	5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.17	Dimensional change warp after ironing without steam	0.27
Dimensional change warp after ironing with steam	0.27	Dimensional change weft	0.14
Dimensional change weft after ironing without steam	0.07	Dimensional change weft after ironing with steam	0.07-

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester Inherent FR	Warp yarn sizes	20 DEN
Warp threads per cm	40.00	Warp turns per meter (TPM)	NA
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

Yarn 2

Weft composition	100% Polyester Inherent FR	Weft yarn sizes	NE 14.3
Weft threads per cm	3.32	Weft turns per meter (TPM)	600
Weft type staple	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

Yarn 3

Weft composition	100% Polyester Inherent FR	Weft yarn sizes	NE 14.3
Weft threads per cm	3.32	Weft turns per meter (TPM)	600
Weft type staple	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes

Yarn 4

Weft composition	100% Polyester Inherent FR	Weft yarn sizes	20 DEN
Weft threads per cm	33.36	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification not textured	Yes		