Lovable



BASIC INFORMATION

Launch Date Delivery time (weeks) special lab di Country of origin Vertical repeat (cm) Horizontal repeat (cm) Roll diameter (in cm, for 50 meters) Double folded face in Average piece length (m) MID TR	Turkey 60 30	Tariff item number Number of colour ways Characteristics Vertical repeat (inch) Horizontal repeat (inch) Roll diameter (in inch, for 50 meter) Minimum for special colour (m) Railroaded	54076990 4 Sheer 23.62 11.81 0 1000 Yes
CATEGORY			
Colouring type Type of print/dye - disperse After treatment - zinc selvedge weig	Yarn dyed Yes ght (g/m) 22	Treatment Zinc selvedge	Thermofixed Yes
Care codes			
Care code for washing (°C) Care code comments also washable at 71°C /160F meetin hospital washing standard AATCC90 $\overbrace{600}^{\circ}$ $\overbrace{000}^{\circ}$ $\overbrace{000}^{\circ}$ $\overbrace{000}^{\circ}$	-	Care code for washing (°F) W	ash at 160°F
Use code - curtains/draperies	Yes	Maritime	Yes
FABRIC TYPE			
Composition 100% Polyeste Weaving type - jacquard Useable width (cm) Full width (cm) Woven FR STANDARDS	r Inherent FR Yes 300.00 302 Yes	Average yarn number Construction Useable width (inch) Full width (inch) Weight (g/m²)	175.44 40x56.5 118.11 118.9 55
AATCC 96 (Complies) AS/NZS 1530.3 (Pass)	Yes Yes	AS/NZS 1530.2 (Pass) BS5867 part 2 type B	Yes Yes



BS5867 part 2 type C (Complies) CAL 19 section 1237.1 EN13773 IMO FTPC PART 7: Textiles and films	Yes Yes Yes Yes	Boston Fire test BFD IX-1 (Pass) DIN 4102 (B1) FMVSS 302 (Pass) M1 France	Yes Yes Yes Yes
ENVIRONMENTAL STANDARD	S		
Oeko-Tex ISO 14001	Yes Yes	Oeko-Tex 1000	Yes
SPECIFICATIONS			
Colour fastness to light	6	Acoustic absorption ISO 354 - ISO 11654 draped D/flat n.a.	
Colour fastness to light - ISO 105-B02	2		
Colour fastness to light	6		
Colour fastness to water - ISO 105-E0)1		
Colour fastness to water	5		
Resistance to domestic washing 60°C	c (indicated in	%) - ISO 6330	
Dimensional change warp Dimensional change weft Colour fastness (ISO 105 C06)	0.93- 0.70- 5	Dimensional change warp after ironing Dimensional change weft after ironing	0.40- 0.33-
Resistance to dry cleaning P (indicate	ed in %) - ISO	105 D01	
Dimensional change warp Dimensional change weft Colour fastness (ISO 105 D01)	0.36- 0.07- 5	Dimensional change warp after ironing Dimensional change weft after ironing	0.07- 0.33-
Dimensional stability (indicated in %)	- ISO 3759		
Dimensional change warp Dimensional change warp after ironing w	0.05- ⁄ith steam	Dimensional change warp after ironing without steam 0.13 Dimensional change weft 0.00	
Dimensional change weft after ironing wi	0.13	Dimensional change weft after ironing wi	



CONSTRUCTION

Yarn 1			
Warp composition 100% Polyester Inherent FR		Warp yarn sizes	20 DEN
Warp threads per cm	40.00	Warp turns per meter (TPM)	NA
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes
Yarn 2			
Weft composition 100% Polyester	Inherent FR	Weft yarn sizes	20 DEN
Weft threads per cm	40.00	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes
Yarn 3			
Weft composition 100% Polyester	Inherent FR	Weft yarn sizes	300 DEN
Weft threads per cm	16.49	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification textured	Yes	Weft not high tenacity	Yes