Lucky



BASIC INFORMATION

Launch Date	01/04/2018	Tariff item number	54076990
Delivery time (weeks) special lab di	p 4	Number of colour ways	5
Country of origin	Turkey	Characteristics	Sheer
Vertical repeat (cm)	15.00	Vertical repeat (inch)	5.91
Horizontal repeat (cm)	30.00	Horizontal repeat (inch)	11.81
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Double folded face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	50	Railroaded	Yes
MID TR	TEXTRABUR		

CATEGORY

Colouring type	Yarn dyed	Treatment	Thermofixed
Type of print/dye - disperse	Yes	Zinc selvedge	Yes

After treatment - zinc selvedge weight (g/m) 22

Care codes

Care code for washing (°C) Wash at 71°C Care code for washing (°F) Wash at 160°F

Care code comments

also washable at 71°C /160F meeting American

hospital washing standard AATCC96











Use codes

Use code - curtains/draperies Yes Maritime Yes

FABRIC TYPE

Composition	100% Polyester In	herent FR	Average yarn number	255.2
Weaving type - ja	acquard	Yes	Construction	40x49.32
Useable width (c	m)	300.00	Useable width (inch)	118.11
Full width (cm)		302	Full width (inch)	118.9
Woven		Yes	Weight (g/m²)	35

FR STANDARDS

AATCC 96 (Complies)	Yes	AS/NZS 1530.2 (Pass)	Yes	
AS/NZS 1530.3 (Pass)	Yes	BS5867 part 2 type B	Yes	

Technical Product Summary



BS5867 part 2 type C (Complies) CAL 19 section 1237.1 FMVSS 302 (Pass) M1 France	Yes Yes Yes Yes	Boston Fire test BFD IX-1 (Pass) DIN 4102 (B1) IMO FTPC PART 7: Textiles and films	Yes Yes Yes
ENVIRONMENTAL STANDARD	S		
Oeko-Tex ISO 14001	Yes Yes	Oeko-Tex 1000	Yes
SPECIFICATIONS			
Colour fastness to light	6	Acoustic absorption ISO 354 - ISO 1165- draped D/	
Colour fastness to light - ISO 105-B0	2		
Colour fastness to light	6		
Colour fastness to water - ISO 105-E	01		
Colour fastness to water	5		
Resistance to domestic washing 40°C	C (indicated in	n %) - ISO 6330	
Dimensional change warp Dimensional change weft Colour fastness (ISO 105 C06)	0.50- 0.27- 4-5	Dimensional change warp after ironing Dimensional change weft after ironing	0.20- 0.20-
Resistance to domestic washing 60°0	C (indicated in	n %) - ISO 6330	
Dimensional change warp Dimensional change weft Colour fastness (ISO 105 C06)	0.93- 0.69- 4-5	Dimensional change warp after ironing Dimensional change weft after ironing	0.60- 0.46-
Resistance to dry cleaning P (indicat	ed in %) - ISC) 105 D01	
Dimensional change warp Dimensional change weft Colour fastness (ISO 105 D01)	0.30- 0.50- 5	Dimensional change warp after ironing Dimensional change weft after ironing	0.20- 0.26-
Dimensional stability (indicated in %)	- ISO 3759		
Dimensional change warp	0.10	Dimensional change warp after ironing w	ithout steam

Technical Product Summary



Dimensional change warp after ironing with steam

Dimensional change weft

0.00

0.20

0.21

Dimensional change weft after ironing without steam

Dimensional change weft after ironing with steam

0.20-

CONSTRUCTION

Yarn 1			
Warp composition 100% Polyester	Inherent FR	Warp yarn sizes	20 DEN
Warp threads per cm	40.00	Warp turns per meter (TPM)	NA
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes
Yarn 2			
Weft composition 100% Polyester	Inherent FR	Weft yarn sizes	20 DEN
Weft threads per cm	39.99	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes
Yarn 3			
Weft composition 100% Polyester	Inherent FR	Weft yarn sizes	300 DEN
Weft threads per cm	9.33	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification textured	Yes	Weft not high tenacity	Yes