

Odeon



BASIC INFORMATION

Launch Date	01/04/2019	Tariff item number	58013700
Delivery time (weeks) special lab dip	3	Number of colour ways	15
Country of origin	Turkey	Characteristics	Velvet
Vertical repeat (cm)	plain	Vertical repeat (inch)	plain
Horizontal repeat (cm)	plain	Horizontal repeat (inch)	plain
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Face in	Yes	Minimum for special colour (m)	500
Average piece length (m)	40	MID	TRTEKTEK4IST

CATEGORY

Colouring type	Piece dyed	Treatment	Calender
Type of print/dye - disperse	Yes	After treatment - none	Yes

Care codes

Care code for washing (°C)	Wash at 71°C	Care code for washing (°F)	Wash at 160°F
    			

Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
Use code - upholstery	Yes	Use code - bed covering	Yes
Use code - accessories	Yes		

FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	13.88
Weaving type - dobby	Yes	Weaving type - pile	Yes
Construction	40x28	Useable width (cm)	138.00
Useable width (inch)	54.33	Full width (cm)	140
Full width (inch)	55.12	Woven	Yes
Weight (g/m ²)	490		

FR STANDARDS

AATCC 96 (Complies)	Yes	ASTM E84 class I or A	Yes
AS/NZS 1530.2 (Pass)	Yes	AS/NZS 1530.3 (Pass)	Yes
BS5867 part 2 type B	Yes	BS5867 part 2 type C (Complies)	Yes
Boston Fire test BFD IX-1 (Pass)	Yes	CAL 117 (Complies)	Yes

CAL 19 section 1237.1	Yes	CAN/ULC-S109 Large flame test	Yes
CAN/ULC-S109 Small flame test	Yes	DIN 4102 (B1)	Yes
EN13773	Yes	FMVSS 302 (Pass)	Yes
IMO FTPC PART 7: Textiles and films	Yes	Japanese L1091	Yes
M1 France	Yes	NFPA 260	Yes
NFPA 701	Yes	NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes
SN 198'898 (Class 5.2)	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes
----------	-----

SPECIFICATIONS

Martindale (rubs)	100000	Colour fastness to light	4-5
Pilling	4	Brush pilling	4-5
Wyzenbeek (double rubs)	200000	Wyzenbeek wire screen (double rubs - residential use, stopped after 15 000 double rubs)	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek test comments	19-000416
Acoustic absorption ISO 354 - ISO 11654	B/C	Wyzenbeek wire screen heavy duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	4-5
--------------------------	-----

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strength warp (N)	37	Tearing strength weft (N)	38
---------------------------	----	---------------------------	----

Tensile strength - ISO 13934-1

Tensile strength warp (N/5cm)	1000	Tensile strength weft (N/5cm)	840
-------------------------------	------	-------------------------------	-----

Seam slippage - ISO 13936-2

Seam slippage warp (mm)	3	Seam slippage weft (mm)	3
-------------------------	---	-------------------------	---

Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	0.03-	Dimensional change warp after ironing	0.00
Dimensional change weft	0.23-	Dimensional change weft after ironing	0.20-
Colour fastness (ISO 105 C06)	5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	0.43-	Dimensional change warp after ironing	0.40-
Dimensional change weft	0.73-	Dimensional change weft after ironing	0.60-
Colour fastness (ISO 105 C06)	4-5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	0.17-	Dimensional change warp after ironing	0.13-
Dimensional change weft	0.23-	Dimensional change weft after ironing	0.26-
Colour fastness (ISO 105 D01)	5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.14	Dimensional change warp after ironing without steam	0.00
Dimensional change warp after ironing with steam	0.13	Dimensional change weft	0.08
Dimensional change weft after ironing without steam	0.00	Dimensional change weft after ironing with steam	0.26-

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester inhe	Warp yarn sizes	300DNY
------------------	---------------------	-----------------	--------

Warp threads per cm	20.00	Warp turns per meter (TPM)	0
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

Yarn 2

Warp composition	100% Poleyster inhe	Warp yarn sizes	NE 20/2
Warp threads per cm	20.00	Warp turns per meter (TPM)	0
Warp type staple	Yes		
Warp not high tenacity	Yes		

Yarn 3

Weft composition	100% Poleyster inhe	Weft yarn sizes	NE 16/1
Weft threads per cm	28.00	Weft turns per meter (TPM)	0
Weft type staple	Yes		
Weft not high tenacity	Yes		