

Requiem






BASIC INFORMATION

Launch Date	01/04/2020	Tariff item number	5801370000
Delivery time (weeks) special lab dip	2	Number of colour ways	5
Country of origin	Turkey	Characteristics	Velvet
Vertical repeat (cm)	34.50	Vertical repeat (inch)	13.58
Horizontal repeat (cm)	35.00	Horizontal repeat (inch)	13.78
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Face in	Yes	Minimum for special colour (m)	300
Average piece length (m)	30	MID	TRTEKTEK4IST

CATEGORY

Colouring type	Piece dyed	Treatment	Thermofixed
Type of print/dye - disperse	Yes	After treatment - none	Yes

Care codes

Care code for washing (°C)	Wash at 71°C	Care code for washing (°F)	Wash at 160°F
    			

Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
Use code - upholstery	Yes	Use code - bed covering	Yes
Use code - accessories	Yes		

FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	17.2
Weaving type - jacquard	Yes	Construction	63x23
Useable width (cm)	140.00	Useable width (inch)	55.12
Full width (cm)	142	Full width (inch)	55.91
Woven	Yes	Weight (g/m²)	500

FR STANDARDS

AATCC 96 (Complies)	Yes	ASTM E84 class I or A	Yes
AS/NZS 1530.2 (Pass)	Yes	AS/NZS 1530.3 (Pass)	Yes
BS5867 part 2 type B	Yes	BS5867 part 2 type C (Complies)	Yes
Boston Fire test BFD IX-1 (Pass)	Yes	BS7176-BS5852 source 5	Yes
CAL 117 (Complies)	Yes	CAL 19 section 1237.1	No

CAN/ULC-S109 Large flame test	Yes	CAN/ULC-S109 Small flame test	Yes
DIN 4102 (B1)	Yes	EN13773	Yes
EN 1021 part 1 and 2	Yes	FMVSS 302 (Pass)	Yes
IMO A652 part 8	Yes	IMO FTPC PART 7: Textiles and films	Yes
M1 France	Yes	NFPA 260	Yes
NFPA 701	Yes	NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes
SN 198'898 (Class 5.2)	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes
----------	-----

SPECIFICATIONS

Martindale (rubs)	70	Colour fastness to light	5-6
Pilling	4-5	Brush pilling	5
Wyzenbeek (DB)	65000	Wyzenbeek cotton duck type heavy upholstery	Yes
Acoustic absorption ISO 354 - ISO 11654	B		

Colour fastness to light - ISO 105-B02

Colour fastness to light	5-6
--------------------------	-----

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4
-------------------------	---

Tearing strength - ISO 13937-3

Tearing strenth warp (N)	39	Tearing strength weft (N)	130
--------------------------	----	---------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp (N/5cm)	2000	Tensile strength weft (N/5cm)	900
-------------------------------	------	-------------------------------	-----

Elongation - ISO 13934-1

Elongation warp (%)	23.5	Elongation weft (%)	16.5
---------------------	------	---------------------	------

Seam slippage - ISO 13936-2

Seam slippage warp (mm)	2	Seam slippage weft (mm)	3
-------------------------	---	-------------------------	---

Resistance to domestic washing 30°C (indicated in %) - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	0.56-	Dimensional change warp after ironing	0.33-
Dimensional change weft	0.26-	Dimensional change weft after ironing	0.20-
Colour fastness (ISO 105 C06)	4-5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	0.66-	Dimensional change warp after ironing	0.60-
Dimensional change weft	0.43-	Dimensional change weft after ironing	0.20-
Colour fastness (ISO 105 C06)	4-5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	0.60-	Dimensional change warp after ironing	0.40-
Dimensional change weft	0.56-	Dimensional change weft after ironing	0.53-
Colour fastness (ISO 105 D01)	4-5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.12-	Dimensional change warp after ironing without steam	0.00
Dimensional change warp after ironing with steam	0.07	Dimensional change weft	0.15-
Dimensional change weft after ironing without steam		Dimensional change weft after ironing with steam	

0.00

0.00

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester inherent FR	Warp yarn sizes	3000DNY
Warp threads per cm	42.00	Warp turns per meter (TPM)	0
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

Yarn 2

Warp composition	100% Polyester inherent FR	Warp yarn sizes	NE 20/2
Warp threads per cm	21.00	Warp turns per meter (TPM)	0
Warp type staple	Yes		
Warp specification not textured	Yes	Warp not high tenacity	Yes

Yarn 3

Weft composition	100% Polyester inherent FR	Weft yarn sizes	NE 20/1
Weft threads per cm	23.00	Weft turns per meter (TPM)	0
Weft type staple	Yes		
Weft specification not textured	Yes	Weft not high tenacity	Yes