

Oracle

BASIC INFORMATION

Launch Date	01/04/2019	Tariff item number	54079200
Delivery time (weeks) special lab dip	3	Number of colour ways	12
Country of origin	Turkey	Characteristics	Texture
Vertical repeat (cm)	plain	Vertical repeat (inch)	plain
Horizontal repeat (cm)	plain	Horizontal repeat (inch)	plain
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Double folded face in	Yes	Minimum for special colour (m)	510
Average piece length (m)	30	MID	TRTEXTRABUR


CATEGORY

Colouring type	Piece dyed	Treatment	Calender
Type of print/dye - disperse	Yes	After treatment - none	Yes

Care codes

Care code for washing (°F)

Wash at 140°F gentle cycle



Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
-------------------------------	-----	----------	-----

FABRIC TYPE

Composition	100% Polyester inherent FR	Average yarn number	8.08
Weaving type - dobby	Yes	Construction	10x11
Useable width (cm)	310.00	Useable width (inch)	122.05
Full width (cm)	312	Full width (inch)	122.83
Woven	Yes	Weight (g/m²)	260

FR STANDARDS

AATCC 96 (Complies)	Yes	AS/NZS 1530.2 (Pass)	Yes
AS/NZS 1530.3 (Pass)	Yes	BS5867 part 2 type B	Yes
BS5867 part 2 type C (Complies)	Yes	Boston Fire test BFD IX-1 (Pass)	Yes
CAL 117 (Complies)	Yes	CAN/ULC-S109 Large flame test	Yes
CAN/ULC-S109 Small flame test	Yes	DIN 4102 (B1)	Yes
EN13773	Yes	FMVSS 302 (Pass)	Yes

IMO FTPC PART 7: Textiles and films	Yes	Japanese L1091	Yes
M1 France	Yes	NFPA 260	Yes
NFPA 701	Yes	NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes
SN 198'898 (Class 5.2)	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

SPECIFICATIONS

Colour fastness to light	5-6	Pilling	4
Brush pilling	4	Acoustic absorption ISO 354 - ISO 11654	C/D

Colour fastness to light - ISO 105-B02

Colour fastness to light	5-6
--------------------------	-----

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	1.29-	Dimensional change warp after ironing	1.64-
Dimensional change weft	0.26-	Dimensional change weft after ironing	0.46-
Colour fastness (ISO 105 C06)	5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	2.58-	Dimensional change warp after ironing	1.97-
Dimensional change weft	0.17-	Dimensional change weft after ironing	0.20-
Colour fastness (ISO 105 C06)	5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	1.33-	Dimensional change warp after ironing	1.39-
Dimensional change weft	0.53-	Dimensional change weft after ironing	0.86-
Colour fastness (ISO 105 D01)	5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.12-	Dimensional change warp after ironing without steam	0.20
Dimensional change warp after ironing with steam	0.67-	Dimensional change weft	0.15-
Dimensional change weft after ironing without steam	0.00	Dimensional change weft after ironing with steam	0.33

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester inherent FR	Warp yarn sizes	778D
Warp threads per cm	10.00	Warp turns per meter (TPM)	0
Warp type filament	Yes		
Warp specification textured	Yes	Warp specification not textured	Yes
Warp not high tenacity	Yes		

Yarn 2

Weft composition	100% Polyester inherent FR	Weft yarn sizes	1252D
Weft threads per cm	11.00	Weft turns per meter (TPM)	0
Weft type staple	Yes	Weft type filament	Yes
Weft specification textured	Yes	Weft specification not textured	Yes
Weft not high tenacity	Yes		