

RE-Boot




BASIC INFORMATION

Launch Date	01/04/2020	Tariff item number	5407720000
Delivery time (weeks) special lab dip	2	Number of colour ways	9
Country of origin	Taiwan	Characteristics	Dimout
Vertical repeat (cm)	Plain	Vertical repeat (inch)	Plain
Horizontal repeat (cm)	Plain	Horizontal repeat (inch)	Plain
Roll diameter (in cm, for 50 meters)	0	Roll diameter (in inch, for 50 meter)	0
Double folded face in	Yes	Minimum for special colour (m)	400
Average piece length (m)	25	MID	TWLIPEN162TAI

CATEGORY

Colouring type	Piece dyed	Treatment	Thermofixed
Type of print/dye - disperse	Yes	After treatment - none	Yes

Care codes

Care code for washing (°C)	Wash at 71°C	Care code for washing (°F)	Wash at 160°F
    			

Use codes

Use code - curtains/draperies	Yes	Maritime	Yes
-------------------------------	-----	----------	-----

FABRIC TYPE

Composition		Average yarn number	49.06
57% Recycled Inherent polyester FR, 43% Inherent polyester FR			
Weaving type - dobby	Yes	Construction	113x43
Useable width (cm)	300.00	Useable width (inch)	118.11
Full width (cm)	302	Full width (inch)	118.9
Woven	Yes	Weight (g/m²)	320
Light transmission	94%		

FR STANDARDS

AATCC 96 (Complies)	Yes	AS/NZS 1530.2 (Pass)	Yes
AS/NZS 1530.3 (Pass)	Yes	BS5867 part 2 type B	Yes
Boston Fire test BFD IX-1 (Pass)	Yes	CAL 117 (Complies)	Yes
CAL 19 section 1237.1	Yes	CAN/ULC-S109 Large flame test	Yes

CAN/ULC-S109 Small flame test	Yes	DIN 4102 (B1)	Yes
EN13773	Yes	FMVSS 302 (Pass)	Yes
IMO FTPC PART 7: Textiles and films	Yes	Japanese L1091	Yes
M1 France	Yes	NFPA 260	Yes
NFPA 701	Yes	NY/NJ Port Authority - FAR 25.853 12 (Pass)	Yes
SN 198'898 (Class 5.2)	Yes	Taiwanese CNS10285-L31961	Yes
UNI 9174 Classe Uno (Pass)	Yes		

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
Bluesign	Yes	GRS	Yes

SPECIFICATIONS

Colour fastness to light	5	Pilling	4
Brush pilling	4-5	Wyzenbeek (DB)	10000
Wyzenbeek wire screen (DB - residential use, stopped after 15 000 DB)	6,000	Wyzenbeek cotton duck type unrated	Yes
Acoustic absorption ISO 354 - ISO 11654	C	Wyzenbeek wire screen light duty	Yes

Colour fastness to light - ISO 105-B02

Colour fastness to light	5
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4-5
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	4-5
-------------------------	-----

Resistance to domestic washing 30°C (indicated in %) - ISO 6330

Dimensional change warp	0.00	Dimensional change warp after ironing	0.00
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00

Resistance to domestic washing 40°C (indicated in %) - ISO 6330

Dimensional change warp	0.53-	Dimensional change warp after ironing	0.26-
Dimensional change weft	0.00	Dimensional change weft after ironing	0.00
Colour fastness (ISO 105 C06)	5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	1.79-	Dimensional change warp after ironing	1.19-
Dimensional change weft	0.96-	Dimensional change weft after ironing	0.93-
Colour fastness (ISO 105 C06)	4-5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	1.19-	Dimensional change warp after ironing	1.52-
Dimensional change weft	0.60-	Dimensional change weft after ironing	0.53-
Colour fastness (ISO 105 D01)	4-5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.00	Dimensional change warp after ironing without steam	0.07
Dimensional change warp after ironing with steam	0.00	Dimensional change weft	0.29-
Dimensional change weft after ironing without steam	0.00	Dimensional change weft after ironing with steam	0.20-

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester inherent FR	Warp yarn sizes	75D
Warp threads per cm	79.00	Warp turns per meter (TPM)	0
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

Yarn 2

Warp composition	100% Polyester inherent FR	Warp yarn sizes	300D
Warp threads per cm	34.00	Warp turns per meter (TPM)	0
Warp type filament	Yes		
Warp specification textured	Yes	Warp not high tenacity	Yes

Yarn 3

Weft composition	100% Polyester inherent FR	Weft yarn sizes	300D
Weft threads per cm	10.00	Weft turns per meter (TPM)	0
Weft type filament	Yes		
Weft specification textured	Yes	Weft not high tenacity	Yes

Yarn 4

Weft composition	100% Polyester inherent FR	Weft yarn sizes	375D
Weft threads per cm	13.00	Weft turns per meter (TPM)	0
Weft type filament	Yes		
Weft specification textured	Yes	Weft not high tenacity	Yes

Yarn 5

Weft composition	100% Polyester inherent FR	Weft yarn sizes	300D
Weft threads per cm	21.00	Weft turns per meter (TPM)	0
Weft type filament	Yes		
Weft specification textured	Yes	Weft not high tenacity	Yes